

# INDEX

MANUAL

DURETÉ

HÄRTE

HARDNESS

Rm [N/mm <sup>2</sup> ]	HB	HRA	HRB	HRC	HV30
300	89				94
400	118		68		124
500	148		81		155
600	177		89		167
700	207		96		218
800	237			22.2	249
900	266			26.9	280
1000	296			31	311
1100	325			34.8	342
1200	354			38.2	373
1300	383			41.2	403
1400	411	72.6		44	431
1485	436	73.7		46	455
1578	461	74.7		48	482
1680	488	75.8		50	511
1800	518	76.8		52	542
	542	77.9		54	577

DURETÉ

HÄRTE

HARDNESS

Rm [N/mm <sup>2</sup> ]	HB	HRA	HRB	HRC	HV30
	571	78.9		56	615
	620	80.0		58	656
	659	81.0		60	701
	701	82.1		62	750
		83.1		64	803
		84.2		66	861
		85.3		68	924
		85.7			1000
		87.0			1100
		88.2			1200
		89.3			1300
		90.4			1400
		91.3			1500
		92			1600
		92.7			1700
		93.3			1800
		93.7			1900